

CARBOPOL®* 934P NF POLYMER

Carbopol® 934P NF polymer meets the limits cited in the current edition of the following monograph:

- United States Pharmacopeia/National Formulary (USP/NF) monograph for Carbomer 934P

Applicable synonyms for Carbopol® 934P NF polymer are carboxypolymethylene and carbomers.

General Product Characteristics

Appearance: White, fluffy powder

Odor: Slightly acetic

Test	Specification	Lot Test Frequency ¹	Test Procedure ²
Identification			
Colorimetric test	Pass	1:200	USP/NF
Gel formation test	Pass	1:200 ³	USP/NF
Carboxylic Acid Content, Assay %	56.0 - 68.0	1:1	Lubrizol 1318-A
Viscosity, cP, 25°C Brookfield RVT, 20 rpm, neutralized to pH 7.3 - 7.8			
0.2 wt% mucilage, spindle #4	2,050 - 5,450	1:1	Lubrizol 430-I
0.5 wt% mucilage, spindle #6	29,400 - 39,400	1:1	Lubrizol 430-I
Loss on Drying, %	2.0 max	1:1	USP/NF
Heavy Metals, ppm			
Total heavy metals, as Pb	20 max	1:200	USP/NF
Specific metals: Hg, Pb, As, Sb	10 max	1:200	Lubrizol SA-012
Residual Solvent⁴, ppm			
Benzene	100 max	1:1	Lubrizol SA-094
Residual Monomer, ppm			
Free acrylic acid	1,000 max	1:1	Lubrizol SA-005

¹ Where lot test frequency is less than 1:1, Lubrizol Advanced Materials, Inc. certifies that each batch/lot meets requirements for the characteristics based on historical process and product data. Because these characteristics are tested on a skip-lot test frequency, results are not reported on the Certificate of Analysis.

² Lubrizol test procedures have been cross-validated to specified compendial procedure(s) or validated if they are included in the monograph.

³ Gel formation is confirmed by the viscosity test procedure (Lubrizol 430-I) for each lot of polymer that is produced. Every 200 lots, the gel formation test is conducted according to USP requirements.

⁴ No other residual solvents as listed in USP/NF <467> (Class 1, 2, 3, Table 4 or any other solvents) or Ph. Eur. 2.4.24 are used in the manufacturing process of this product. Since the monograph specifies a limit for benzene, the Residual Solvents test <467> limit for benzene is superseded by the monograph limit.

Lubrizol Advanced Materials, Inc. / 9911 Brecksville Road, Cleveland, Ohio 44141-3247 / TEL: 800.379.5389 or 216.447.5000

Lubrizol Advanced Materials, Inc. cannot guarantee how the product(s) will perform in combination with other substances or in the user's process. Therefore, no representations, guarantees or warranties of any kind are made as to the suitability of this product(s) for particular applications. End product performance is

the responsibility of the user. Lubrizol Advanced Materials, Inc. shall not be liable for and the customer assumes all risk and liability of any use or handling of any material beyond Lubrizol Advanced Materials' direct control. The SELLER MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING,

BUT NOT LIMITED TO, THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein is to be considered as permission, recommendation, nor as an inducement to practice any patented invention without permission of the patent owner.

For further information, please visit www.pharma.lubrizol.com